

PRODUCT INSTRUCTIONS: SUPER COVER INKS

Screen Printing

Print ink in method desired and cure. Recommended curing time for Tintex Super Cover Ink is 4 minutes @ 150oC or 6 minutes @ 130oC.

Fabric Painting

Thicken Tintex Super Cover Ink with a small amount of Tintex Thickener if desired. Paint design onto fabric. Dry in sunlight. Place brown paper over design and iron with a hot iron for 3 minutes to finish curing of ink.

Wash Screens and utensils out with water. Store inks sealed in cool dry place. Shelf life will vary according to storage conditions.